



# ACCELGUARD® 80

NON-CHLORIDE, ACCELERATING & WATER REDUCING ADMIXTURE

EUCLID CHEMICAL

## DESCRIPTION

**ACCELGUARD 80** is an accelerating and water reducing admixture for concrete that does not contain calcium chloride. It improves properties of plastic and hardened concrete, provides a significant improvement in early stiffening and setting characteristics, improved workability and decreased bleeding and segregation. This admixture is compatible with air-entraining admixtures, HRWR admixtures (super plasticizers), and conventional water reducing admixtures. ACCELGUARD 80 is effective at all temperatures but is particularly effective above 50°F (10°C).

## PRIMARY APPLICATIONS

- Cold weather concreting
- Structural and plain concrete
- Concrete block and mortar
- Precast and post tensioned concrete

## FEATURES/BENEFITS



- Reduces initial set 1 to 4 hours depending on concrete temperatures
- Improves workability and provides denser concrete
- Minimizes bleeding and segregation
- Improves compressive strength development at early ages
- Decreases overtime allowing earlier finishing
- Increases protection for reinforcement in concrete

## TECHNICAL INFORMATION

### Performance Data

The following test results were achieved using typical ASTM C 494 mix design requirements, 517 lb/yd<sup>3</sup> (307 kg/m<sup>3</sup>) cement content and similar (± 0.5)% air content.

These results were obtained under laboratory conditions with materials and mix designs meeting the specifications of ASTM C 494. Changes in materials and mix designs can affect the dosage response of ACCELGUARD 80.



## PACKAGING

ACCELGUARD 80 is packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums and 5 gal (18.9 L) pails.

## SHELF LIFE

2 years in original, unopened package.

## SPECIFICATIONS/COMPLIANCES

- Fully complies with ASTM C 494, Type C and E admixture specifications
- Fully complies with AASHTO M 194
- ACI 201, Guide for Durable Concrete and ACI 302 Guide for Concrete Floor and Slab Construction prohibit the use of chlorides in many types of concrete. ACCELGUARD 80 may be used in these types of concrete such as, floors over prestressed concrete or galvanized decking, floors containing two kinds of embedded metal, reinforced concrete in moist environments and/or exposed to chloride deicing salts
- ANSI/NSF STD 61 registered

## DIRECTIONS FOR USE

The typical dosage range for ACCELGUARD 80 is 12- 90 oz per 100 lbs (780 - 5870 mL/100kg) of cementitious material. Higher dosages are acceptable with prior testing and confirmation of the desired performance with specific materials being used.

ACCELGUARD 80 should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement. For ambient temperatures below 50°F (10°C) follow ACI 306 Cold Weather Requirements.

## PRECAUTIONS/LIMITATIONS

- ACCELGUARD 80 will freeze at temperatures of approximately -15°F (-26°C). Freezing and thawing will not harm the material if thoroughly agitated.
- Do not use air for agitation.
- Do not dispense directly onto dry cement.
- Do not use ACCELGUARD 80 with Chemcomp Cement or other modified cements without consulting The Euclid Chemical Company.
- Keep concrete from freezing until a minimum of 500 psi (3.5 MPa) is achieved.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.14

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.