



EUCLID CHEMICAL

EUCON CIA

CORROSION INHIBITING ADMIXTURE

DESCRIPTION

EUCON CIA is a Calcium Nitrite based admixture designed to inhibit the corrosion of steel reinforcement in concrete that complies to ASTM C1582 and ASTM C 494 Type C and E. This product contains a 30% Calcium Nitrite solution. When used at recommended dosage rates, this product introduces the proper, industry recognized amount of anodic inhibitor.

PRIMARY APPLICATIONS

- Exterior steel reinforced concrete
- Structural and plain concrete
- Parking decks and exposed balconies

FEATURES/BENEFITS

- Calcium Nitrite based formula used for many years in the concrete industry
- Chemically inhibits the corrosion process
- Reduces the need for additional accelerating admixtures in cold weather
- Compatible with other commonly used Euclid Chemical admixtures
- Dosage rate is directly related to expected chloride concentration
- Increases protection for reinforcement in concrete

TECHNICAL INFORMATION

Typical Engineering Data

The following results were developed under laboratory conditions.

Specific Gravity 1.27 to 1.33
 Unit Weight..... 10.4 to 11.3 lb. /gal
 Freezing point 0°F (-18°C)

Slump

EUCON CIA has little effect on the slump of concrete.

PACKAGING

EUCON CIA is packaged in bulk, 275 gal (1041 L) totes, and 55 gal (208 L) drums.

SHELF LIFE

2 years in original, unopened container.

SPECIFICATIONS/COMPLIANCES

- ASTM C1582
- ASTM Classification C 494 Type C and E
- AASHTO Classification M 194 Type C
- Corps of Engineers Classification CRD C87 Type C

DIRECTIONS FOR USE

Mix Designs

It is strongly recommended the mix trials be run before the start of job site pours. This will allow the ready-mix concrete producer to determine the proper batching sequence and the required dosage of other admixtures needed to deliver the specified concrete mix to the job site.

EUCON CIA may be added with the concrete batch water. It should not be mixed with any other admixture prior to being introduced into the concrete mixer. Mix designs are supplied upon request.

Dosages

Corrosion Inhibitor

The recommended addition rates range for Eucon CIA Corrosion Inhibitor is from 2 - 6 gal/yd³ (10 - 30 L/m³). The Chloride to Nitrite ratio is important. The project specification will indicate or specify the amount of chloride ions protection necessary. The dosage rate of EUCON CIA is directly related to the level of chloride protection and can be chosen from Table 1. EUCON CIA will accelerate concrete setting times at all recommended dosages. To counteract this acceleration use a retarder such as EUCON RETARDER 75 or EUCON RETARDER 100, as shown in Table 2.

When no specified chloride ion protection level is specified contact your local Euclid sales representative.

Set Acceleration

If used as an accelerator the Eucon CIA dosage range is 10 - 90 oz/cwt (650 - 5870 mL per 100 kg) of cementitious materials.

Mix Water Reduction:

It is necessary to adjust the mix water to account for the water in EUCON CIA, Subtract 7.0 lbs. or 0.85 gallons of water per gallon of EUCON CIA.

Table 1

EUCON CIA Dosage Rates vs Chloride Protection

EUCON CIA gal/ yd ³	Chloride lbs. / yd ³
2.0	6.0
2.5	8.0
3.0	9.9
3.5	11.5
4.0	13.0
4.5	14.1
5.0	15.6
6.0	16.0

Table 2

EUCON CIA Dosage Rates vs Retarder 100 dosage

EUCON CIA gal/ yd ³	Retarder 100@70°F oz./cwt.
3.0 to 4.0	3 to 5
4.0 to 5.5	4 to 7
5.5 to 6.0	5 to 8

CLEAN-UP

Clean tools and equipment with water before concrete hardens.

PRECAUTIONS / LIMITATIONS

- Store at temperatures above 0°F (-18°C). When EUCON CIA freezes, its corrosion inhibition is completely restored by thawing and thorough agitation.
- Do not dispense directly onto dry cement.
- Quality concrete is necessary to slow the ingress of chloride into the concrete. According to ACI 318, the "Building Codes Requirements for Reinforced Concrete" requires certain design constraints, such as maximum water to cement ratio and providing adequate cover over the reinforcing steel. All pertinent codes and guides should be consulted prior to final approval of mix design.
- Additional protection can be achieved by using high range water reducing admixtures (such as EUCON 37) to reduce the water to cement ratio. Also, the use of EUCON MSA, a silica fume admixture can be used to reduce concrete permeability.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.17

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.