

SURFHARD®

LIQUID DENSIFIER AND DUSTPROOFER FOR CONCRETE

DESCRIPTION

SURFHARD® is a water-based magnesium silicofluoride solution that reacts chemically with alkaline materials in concrete to produce a more dense, durable, and chemically resistant floor. SURFHARD is especially effective at strengthening weak, soft, or dusting concrete surfaces. A patented penetrating agent in SURFHARD assists in its penetration and reactivity, enabling SURFHARD to dustproof and densify at a greater depth.

PRIMARY APPLICATIONS

- Concrete floors, especially those with carbonated, soft, or dusting surfaces
- Schools
- Industrial floors
- Commercial buildings
- Residential basements

FEATURES/BENEFITS

- Densifies and dustproofs concrete surfaces
- Prolongs floor life
- Resists acids, alkalis, oils and salts
- Improves concrete that is carbonated, soft, or powdery
- Can be used without interrupting production schedules
- ♣ Can contribute to LEED points

TECHNICAL INFORMATION

Typical Performance

Application	Cure Time
Foot traffic	4 to 6 hours
Wheel traffic.....	4 hours
VOC Content	0 g/L

SURFHARD helps protect concrete against the harmful effects of:

- Caustic soda
- Calcium chloride
- Sodium chloride
- Soap solutions
- Ammonium chloride
- Solvents
- Fuel oils
- Sugar solutions

Appearance: SURFHARD is a clear liquid that does not change the color or appearance of concrete. Immediately after application, the color of the treated concrete may initially appear darker. As the sealer cures and dries out, the treated concrete will have little change in appearance. Treated concrete will slightly bead water and other liquids.

PACKAGING

SURFHARD is packaged in 55 gal (208 L) drums and 5 gal (18.9 L) pails.

SHELF LIFE

2 years in original, unopened package.

SPECIFICATIONS/COMPLIANCES

- USDA compliant



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



COVERAGE

SURFHARD is applied in up to three coats per the following recommended dilutions:

Coat	Dilution
1st coat	1 part SURFHARD to 2 parts water
2nd coat	1 part SURFHARD to 1 part water
3rd coat	2 parts SURFHARD to 1 part water

Coverage Rate	Undiluted Surfhard	Diluted Surfhard
1st coat:	900 ft ² /gal (22.1 m ² L)	300 ft ² /gal (7.4 m ² L)
2nd coat:	400 ft ² /gal (9.8 m ² L)	200 ft ² /gal (4.9 m ² L)
3rd coat:	225 ft ² /gal (5.5 m ² L)	150 ft ² /gal (3.7 m ² /L)

All coverage rates are approximate

DIRECTIONS FOR USE

Surface Preparation: The surface to be treated should be clean, free of curing compounds, sealers, paint or any other contaminants that could prohibit penetration of SURFHARD. Membrane forming curing compounds should not be used on new concrete if SURFHARD is to be applied, unless a dissipating curing compound such as KUREZ DR VOX is used and cleaned off the surface after the curing period. For best performance, concrete should be dry before applying SURFHARD. New concrete surfaces should be at least 7 days old prior to application. Extremely soft and porous surfaces should be saturated with water prior to application. When the surface is dry, apply the 1st coat of SURFHARD and proceed as indicated under Placement below. This pre-wetting concentrates the chemical at the top level of the concrete. The final coat will then harden at the top surface and yield maximum wearing and resistance qualities. In some instances, or in some selected areas, a surface may require an additional application of undiluted SURFHARD to complete hardening and dustproofing.

Mixing: SURFHARD is easily diluted in water with mild agitation.

Placement: Flood each coat of SURFHARD onto the surface and spread with a soft fiber broom, squeegee, or mop. Allow the solution to soak into the concrete for 10 to 15 minutes and redistribute any puddles that remain. Treated surfaces should be thoroughly dry between coats. Drying time may vary from 4 to 12 hours depending upon the temperature, humidity, and whether the concrete is indoors or outdoors. As the various coats of SURFHARD are applied, each succeeding coat will yield increased coverage because the concrete surface is in the process of hardening and becoming more dense. After the third coat the floor should be thoroughly flushed with water and scrubbed with a stiff broom to remove any residual material. If the floor should show patches of white upon drying, immediately flood with water and scrub the floor with a mechanical scrubber, rinse and dry. Do not attempt further treatment.

NOTE: All three coats may not be necessary to harden the floor. If the floor should show patches of white on drying, immediately flood with water and scrub the floor with a mechanical scrubber, rinse and dry. Do not attempt further treatment.

CLEAN-UP

Clean brushes, tools, equipment and flush sprayer with potable water immediately after use.

PRECAUTIONS/LIMITATIONS

- SURFHARD is not recommended for application to colored concrete surfaces.
- Allow the product to dry 4 to 6 hours at 70°F (21°C) before exposure to traffic or rain.
- SURFHARD is a water-based material and must be kept from freezing.
- If excess SURFHARD is left on the concrete surface, a white residue may form and should be removed by scrubbing immediately. If this residue is allowed to dry, removal may require mechanical means such as sanding or grinding.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 10.09

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.