

INCRETE COLOR-CRETE™ 7 FOR 28

Pre-Packaged Powder Integral Color for Concrete



EUCLID CHEMICAL



Tan - Light
1 Bag/2 Yards



Tan - Medium
1 Bag/1 Yard



Tan - Dark
2 Bags/1 Yard



Tan - Heavy
4 Bags/1 Yard



Cayenne - Light
1 Bag/2 Yards



Cayenne - Medium
1 Bag/1 Yard



Cayenne - Dark
2 Bags/1 Yard



Cayenne - Heavy
4 Bags/1 Yard



Black Oxide - Light
1 Bag/2 Yards



Black Oxide - Medium
1 Bag/1 Yard



Black Oxide - Dark
2 Bags/1 Yard



Black Oxide - Heavy
4 Bags/1 Yard



Natural Brown - Light
1 Bag/2 Yards



Natural Brown - Medium
1 Bag/1 Yard



Natural Brown - Dark
2 Bags/1 Yard



Natural Brown - Heavy
4 Bags/1 Yard



Saddle (Yellow) - Light
1 Bag/2 Yards



Saddle (Yellow) - Medium
1 Bag/1 Yard



Saddle (Yellow) - Dark
2 Bags/1 Yard



Saddle (Yellow) - Heavy
4 Bags/1 Yard



Red - Light
1 Bag/2 Yards



Red - Medium
1 Bag/1 Yard



Red - Dark
2 Bags/1 Yard



Red - Heavy
4 Bags/1 Yard



Bark - Light
1 Bag/2 Yards



Bark - Medium
1 Bag/1 Yard



Bark - Dark
2 Bags/1 Yard



Bark - Heavy
4 Bags/1 Yard

*Also Available in Chrome Green

Color shown approximates laboratory samples made with Type-1 portland, tan sand, COLOR-CRETE™ pigment and 4 in (10 cm) slump, unsealed. Due to variations of job site conditions, actual colors can and will vary slightly from those on the color chart. Conditions that will cause variation are inconsistent slump (water content), finishing and curing methods, weather conditions, and concrete raw materials, especially in the lower pigment loadings (light, medium). A job-site or test slab sample should be made using specified materials and the finishing and curing techniques to be used. For color consistency, batch to batch uniformity must be maintained.

INCRETE COLOR-CRETE™ 7 FOR 28

Pre-Packaged Powder Integral Color for Concrete

Best Practices and Procedures

Basic Use

COLOR-CRETE™ 7 FOR 28 is designed for use in all cementitious materials, producing unlimited color effects. The primary applications are cast-in-place, slab-on-grade, precast, tilt-up, concrete pavers and roof tiles. COLOR-CRETE 7 FOR 28 can also be used in concrete curbing, stucco, cast stone and plaster.

Composition

Euclid Chemical colors are pure synthetic iron-oxide pigments, manufactured to the highest standards. They are high strength and uniform in color and exceed ASTM C979 specifications for integrally-colored concrete. COLOR-CRETE 7 FOR 28 colors are light-fast, lime-proof and totally weather-proof providing a permanent color-fast solution.

Packaging

COLOR-CRETE 7 FOR 28 is packaged in 6 lb (2.7 kg) water-soluble bags.

Specify Color-Crete 7 For 28

By Name _____

As manufactured by Euclid Chemical at the rate of _____ bags per yd³ (m³) of concrete.

Mix Design

Design concrete mixes to use the lowest water/cementitious ratio applicable for local conditions and materials. Type I, II, or V Portland Cement is recommended. When appropriate, use in combination with Supplementary Cementitious Materials (SCM's) such as Class F Fly Ash, Natural Pozzolan, or Ground Granulated Blast Furnace Slag. When SCM is used, use throughout the project for consistent color. Place concrete with a 4" slump (not to exceed 5"). If a higher slump is required use a mid-range or high-range water reducing admixture. Do not use admixtures containing calcium chloride. Placement slump should be appropriate for the application, non-segregating and consistent from batch to batch. A jobsite test batch placement is recommended using a minimum batch size that is 1/3 of the capacity of the mixing equipment using the same mix design, raw materials, slump, placement and finishing techniques that will be used on the actual job. Contact your local Euclid Chemical representative for technical assistance.

Adding Powder Pigments

Ideally the best procedure is to batch 40-50% of the load. With the mixer running, add color and mix for 1-2 minutes before adding the balance of materials. Once all materials have been added, mix the drum at mixing speed for 5 minutes. Be sure to use the same mix design and slump (4") from truck to truck. If higher slump is required, it can be obtained using a water reducing admixture. It's important to consistently use the same cement, as different cements can vary in color, thus affecting the final color. Watch the slump closely, as varying slumps can be an indication of water-to-cement ratio inconsistency that can affect final color. Never add Color-Crete to an empty drum or mixer.

At the Plant: Backspin the drum to make sure it is empty, because residual concrete and extra water will affect color. Add COLOR-CRETE 7 FOR 28 after headwater has been loaded. Never add color to a dry drum.

On the Job Site: Add COLOR-CRETE 7 FOR 28 directly into the mix. Avoid hitting the drum blades. Mix at charge speed for 10-12 minutes (minimum 75 revolutions). Bring enough concrete onto the chute to check for ribboning. Mix longer if necessary.

Be sure to use the mix design and slump (4 in/10 cm) from truck to truck (if higher slump is required it may be obtained by the use of water reducing admixtures). It is important to use the same cement because different cements may have different shades of gray that can affect final color. Watch the slump closely because varying slumps are an indication of varying water-cement ratios, and this can affect final color.

Job Site Samples

A representative job site sample should be produced for each color and/or mix design. These job site samples should be of adequate size to be representative of the actual job and produced with a minimum of 3 yd³ (2.3 m³) or 1/3 the capacity of the mixer. These samples should be cast using the same aggregates, cement, water-cement ratio and finishing techniques to be used on the job. These samples should also be produced and approved prior to starting the first pour on the site.

Job Site Prep

Concrete should be placed over a properly placed and compacted subgrade. This subgrade should be free of mud, standing water, and frost. If placing over inconsistent subgrades such as wood, plastic, asphalt or existing concrete, know that this will affect the evaporation rate and cure time of the concrete, which can increase the likelihood of efflorescence and cause color variation.

Placing, Finishing and Curing

Concrete must be placed with consistent slump not exceeding 5 in (12.7 cm) maximum.

Troweling may begin after bleed water evaporates. Concrete should be stiff or plastic before troweling or brooming. Hard or late troweling will cause burns or dark spots.

Do not add water or other foreign materials to surface upon finishing or discoloration will occur.

For exterior installations, apply rotary, broom or other uniformly textured finish for both appearance and slip resistance. Broom, rotary and rough finishes will usually cure more even-colored than smooth troweled surfaces.

Evaporation of water can cause a white hazy film (efflorescence) on the surface of concrete. Efflorescence is more noticeable on colored concrete surfaces giving the appearance of a chalky or faded look. This effect can be reduced or eliminated by proper curing and protection against water penetration.

Efflorescence can be removed with mild acid cleaners formulated to remove efflorescence. Follow manufacturer instructions and

always test a small area to insure product will not discolor or etch the surface.

Proper curing is essential to the strength and durability of the finished concrete. Euclid Chemical recommends the use of Super Diamond Clear and Super Diamond Clear 350 as a curing agent to promote proper hydration and strength gain. Please check with Euclid Chemical for the various formulas available in your area. Until it is completely cured, the color of concrete is normally less uniform and sometimes darker than the final color. Allow 28 days for full cure.

Limitations

Variations in cement color, type and brand can all produce variations in the final color. Variations in aggregates, finishes, forming materials and methods as well as curing can all affect the final color. It is very important to keep all materials, operations and techniques as consistent as possible. Calcium chloride should not be added to any concrete containing COLOR-CRETE 7 FOR 28 as it can cause discoloration in the finished product.

Vertical Concrete

Prior to pouring, a job site sample should be cast. Whenever using new forms, they should be seasoned with a slurry of matching color. Please contact Euclid Chemical for more information on matching slurries. All holes, plugs, gaps and joints should be patched or filled to prevent water leaking out of these areas. If this is not performed, the water-cement ratio in the area near the leaks will change and discolor the surface. If using internal vibrators, be careful not to allow the vibrator head to come in contact with reinforcing steel or the face of the form because this can create a dark spot on the surface known as a vibrator burn. If using form liners, be sure to remove any cement paste from previous pours and to clean prior to each pour. When pouring integrally-colored concrete, always use a non-staining, form-release agent. To help achieve more color consistency, all forms should be stripped when concrete is of same age.

Maintenance

Integrally-colored concrete can be maintained by sweeping. Spills should be cleaned up as they occur. Dirt may be rinsed with clean water. Heavily soiled areas may be scrubbed with water and a stiff bristle brush. Heavily soiled areas may be scrubbed with water and a stiff bristle brush. A concrete degreaser can be used to remove most stubborn stains. For maintenance of large areas, auto scrubbers may be used. To maintain surfaces that have been sealed with one of Euclid Chemical's acrylic sealers please refer to the Technical Data sheets for the particular sealers used.

Technical Support

The Euclid Chemical color service laboratory is available to provide expert assistance for your color needs.

INCRETE COLOR-CRETE COLORS

All colors shown on this chart are represented as closely as possible. Upon installation, variations can be expected due to differences in cement, aggregates, method of application and light sources.

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

CHART CC-36



EUCLID CHEMICAL

1611 Gunn Highway

Odessa, FL 33556

1-800-752-4626

www.euclidchemical.com

CC36 Increte Color-Crete™ 7 for 28 © 2021 The Euclid Chemical Company. All rights reserved. This material is provided for informational purposes only. The Euclid Chemical Company expressly disclaims any liability relating to the use of this material. Nothing stated herein shall give rise to or constitute any warranty by The Euclid Chemical Company, express or implied, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. The information provided in this material is not intended to be all inclusive, as the manner in which any product is used or handled may involve other or additional considerations that are not addressed herein.