



INCRETE COLOR-CRETE

Admixture for Color Conditioned Concrete

Description

INCRETE COLOR-CRETE is a concentrated color admixture, available in powder, granular, or liquid form. INCRETE COLOR-CRETE is designed to be used in all cementitious materials, producing a wide variety of color effects.

Primary Applications

- Base color for stamped concrete
- Manufactured concrete pavers
- Cast stone and roof tiles
- Cast-in-place slabs on grade
- Tilt-up panels, pre-cast concrete
- Stucco, plaster

Technical Information

INCRETE COLOR-CRETE is composed of high-grade materials, including specific synthetic iron-oxide pigments chosen for intense, uniform color while exceeding ASTM C 979 specifications for integrally colored concrete.

INCRETE COLOR-CRETE powder is produced in 35 standard colors. Custom colors, in all three forms, are also available upon request.

Packaging

INCRETE COLOR-CRETE is available in several forms from batch-ready powder to liquid. Batch-ready pulpable bags and INCRETE COLOR-CRETE LIQUID are pre-packaged to contain an exact measurement of pigment that can be added directly to ready-mix drums.

Batch-ready bags are available in premeasured amounts convenient for 5 or 6 sack mixes.

Euclid Chemical will custom package all powder colors in batch-ready bags in increments of 1 lb (0.45 kg), 5 lb (2.26 kg), or 25 lb (11.34 kg).

INCRETE COLOR-CRETE LIQUID and INCRETE COLOR CRETE GRANULAR pigments are dispensed on-site or at ready-mix plants using the COLOR-MATIC dispensing systems.

Shelf Life

INCRETE COLOR-CRETE Powder and Granular: Unlimited, in original, unopened container.

INCRETE COLOR-CRETE LIQUID: 6-12 months in original, unopened container.

Specifications/Compliances

Meets or exceeds ASTM C 979 requirements.

Directions for Use

APPLICATION PROCESS

Consult the Best Practices and Procedures Guide for Integrally Colored Concrete.

Mix Design: Use a minimum cement content of 470 lb/yd³ (280 kg/m³), which is a 5-bag mix. Design for the lowest slump that can be placed and finished, but no greater than 5 in (12.7 cm). Type II cement is preferred, and cementitious substitutes, such as fly ash or slag, are not recommended for color consistency. Do not use calcium-chloride admixtures. A test patch at the job site is recommended using at least a 3 yd³ (2.29 m³) mix. Use the same mix design, raw materials, placement, and finishing techniques that will be used on the actual job.

Batching And Mixing: Cement substitutes, such as fly ash or slag, should not be used. Contact your local Euclid Chemical representative for suggestions. With the mixer running add the color and mix for 1-2 minutes before adding the balance of materials. Once the balance of materials has been added, mix the drum at mixing speed for five minutes. Never add INCRETE COLOR-CRETE to an empty drum/mixer. For consistent batches, use the same mix design and slump from truck to truck. (If higher slumps are required a water-reducing admixture may be used.) Track the slump between batches, because different water-to-cement ratios can affect the final color. It is important to use the same cement because different cements may be different shades of gray, thereby affecting the final color of the concrete.

Forming & Placing Concrete For Vertical Surfaces: Seal joints in forms for vertical surfaces. Water leakage at joints causes changes in water-to-cement ratio and discoloration near the leak.

Precautions/Limitations

- Concrete placed in the sun sets at a different rate than concrete in the shade. This may cause differences in color. If possible, time the pour to avoid having sunlit and shaded areas.
- Do not add water to the surface during finishing operations. Added water may create a blotchy surface.
- High slumps may result in non-uniform color.
- Do not use calcium-chloride admixtures.
- For professional use only.
- In all cases, consult the Safety Data Sheet before use.

Rev. 04.20

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.