



# EUCOCRETE SUPREME

POLYMER MODIFIED, HIGH PERFORMANCE CONCRETE  
WITH CORROSION INHIBITOR

## PACKAGING

50 lb (22.7 kg) bags  
Code: 0655 50

Bulk bags suitable for mixing in ready-mix trucks available (MTO)

## APPROXIMATE YIELD

**50 lb (22.7 kg) unit:** 0.37 ft<sup>3</sup> (0.01 m<sup>3</sup>) per unit when mixed with 0.5 gallons (1.9 L) of potable water.

**Extended:** 0.46 ft<sup>3</sup> (0.013 m<sup>3</sup>) per unit when extended with 15 lbs (6.8 kg) of pea gravel. See full extending instructions under "Directions for Use".

## MINIMUM/MAXIMUM APPLICATION THICKNESS

Neat: 1 to 6 inches (2.5 to 15 cm)

Extended: 6 inches (15 cm) or more

## CLEAN UP

Clean tools and equipment with water before the material hardens.

## SHELF LIFE

2 years in original, unopened package

## DESCRIPTION

EUCOCRETE SUPREME is a versatile, single-component, latex and microsilica modified, repair mortar containing a migratory corrosion inhibitor, designed to provide protection from corrosion for repair projects of all types. Requiring only the addition of water, EUCOCRETE SUPREME is a high strength material which is easy to use with an extended working time for ease of placement. It is similar in appearance to concrete and is suitable for use as a topping or repair mortar on horizontal surfaces and formed vertical and overhead repairs.

## PRODUCT CHARACTERISTICS

### FEATURES/BENEFITS

- Microsilica modified for high strength
- Pre-mixed with pea gravel, ready-to-use
- Low permeability with excellent freeze/thaw resistance
- Contains an integral corrosion inhibitor
- Applications from 1" (2.5 cm) to full depth
- Interior or exterior
- Form and pour repairs

### COMMON METHODS

- Trowelable (horizontal applications)
- Pumpable
- Form and pour

### PRIMARY APPLICATIONS

- Parking decks
- Joint repairs
- Balconies
- Equipment bases
- Pavements
- Beams
- Form & pour jobs

### APPEARANCE

EUCOCRETE SUPREME is a free-flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear somewhat darker than the surrounding concrete. While this color will lighten up substantially as the concrete cures and dries out, the repair may always appear slightly darker than the surrounding concrete.

The following coverage rates are approximations based on yield of a 50 lb unit mixed at standard consistency.

Application Thickness (inches)	1	1 1/2	2	3	4	6
Coverage Area per Unit (ft <sup>2</sup> )	4.4	2.9	2.2	1.4	1.1	0.7

## TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109	Compressive Strength 2" (50 mm) cubes @ 0.5 gal/50 lb bag	1 day . . . . . 4,200 psi (30 MPa) 7 days . . . . . 7,250 psi (50 MPa) 28 days . . . . . 10,300 psi (71 MPa)
ASTM C39	Compressive Strength 3" x 6" cylinder @ 0.5 gal/50 lb bag	1 day . . . . . 4,530 psi (31 MPa) 7 days . . . . . 6,820 psi (47 MPa) 28 days . . . . . 8,500 psi (59 MPa)
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles . . . 81% relative dynamic modulus
ASTM C348	Flexural Strength	7 days . . . . . 950 psi (6.6 MPa) 28 days . . . . . 1,050 psi (7.2 MPa)
ASTM C1202	Rapid Chloride Permeability	28 days . . . . . 437 coulombs
	Unit Weight	Approximately 145.0 lb/ft <sup>3</sup> (2323 kg/m <sup>3</sup> )
	Consistency	Slump Cone. . . . . > 9 inches (229 mm)
ASTM C403	Set Time	Initial . . . . . approximately 6 hours Initial . . . . . approximately 7 hours
	Volumetric Resistivity	28 days . . . . . 34,275 ohm-cm

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

---

## DIRECTIONS FOR USE

**Surface Preparation:** Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 5-7 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

**Priming & Bonding (Saw Cut & Chipped Out Repairs, Form & Pour Repairs):** Thoroughly clean any exposed reinforcing steel, and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of EUCOCRETE SUPREME to the saturated surface dry (SSD) concrete surface may be used for bonding. The repair material must be placed on the scrub coat before the scrub coat dries out.

**Mixing:** All materials should be in the proper temperature range of 60°F (15°C) to 90°F (32°C). Single 50 lb (22.7 kg) bags may be mixed with a drill and “jiffy” mixer. Use a horizontal shaft, paddle type mortar mixer for mixing multiple bags simultaneously. Add the appropriate amount of water, 0.45 - 0.50 gal (1.7 - 1.9L) per bag, for the batch size and then add the dry product. Mix a minimum of 3 minutes. If additional pea gravel is to be added, mix an additional 2 to 3 minutes. For deeper repairs over 6” (15 cm), extend Eucocrete Supreme with 15 lb (6.8 kg) of clean, SSD, 3/8” (9.5 mm) rounded pea gravel (#8, ASTM C33). The pea gravel must be dense and non-absorbive per ASTM C127 and non-reactive (ASR) per ASTM C227, C289 and C1260.

**Mixing Bulk Bags:** Add the additional pea gravel, if desired, and approximately 80% of the appropriate water for the batch size to the ready-mix concrete truck. Fully open the top of the bulk bag. Position the bulk bag over the truck opening using a forklift or crane. While the drum is turning at slow speed, cut the bottom of the bulk bag to release contents into truck. Use the remaining mix water to wash down any dry, stuck material into the drum. Mix for a minimum of 5 minutes after last bulk bag is added. Reverse drum and check consistency. Note: It is recommended to keep 50 lb (22.7 kg) bags on hand to adjust consistency if needed. The mixed product should be transported to the repair area and placed immediately.

**Placement:** For patching, spread with a trowel, come-a-long, or square tipped shovel to a thickness that matches the surrounding concrete. **Note:** On large floor areas, use screed strips as guides in combination with vibratory screeding to level. Compact and finish by hand or machine trowel.

**Finishing:** This product is designed for finishing with a float or broom. A steel trowel finish may be applied, but timing of the final trowel is critical and the contractor may have difficulty achieving a smooth finish over a large area. Do not add water to the surface during the finishing operation; use EUCOBAR evaporation retarder.

**Curing and Sealing:** To prevent surface cracking, cure the repair with a curing and sealing compound from The Euclid Chemical Company, or cure a minimum of three days with a moisture retaining covering, such as polyethylene film. In hot, windy or direct sunlight situations, re-wet the surface and cover with a moisture retaining covering.

---

## PRECAUTIONS/LIMITATIONS

- Do not use material at temperatures below 45 °F (7 °C).
- When necessary, follow the recommendations in ACI 305R “Guide to Hot Weather Concreting” or ACI 306R “Guide to Cold Weather Concreting”.
- No heavy traffic until the product has fully cured.
- Keep repair from freezing until a minimum strength of 1,000 psi (6.90 MPa) is reached.
- In all cases, consult the Safety Data Sheet before use.

Rev. 09.23

---

**WARRANTY:** The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.