

GROUTS

Master Format #: 03 62 13

NS GROUT

NON-SHRINK, NON-STAINING, NON-METALLIC GROUT



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bags and pails

Code: 088 50 (bag)

Code: 088 05 (pail)

APPROXIMATE YIELD

50 lb (22.7 kg) unit: 0.45 ft³ (0.013 m³) per unit when mixed with 1.2 gal (4.6 L) of potable water.

Extended*: 0.66 ft³ (0.019 m³) per unit

*See full extending instructions under "Directions for Use".

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

2 years in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- CRD-C 621, Corps of Engineers Specification for Non-Shrink Grout
- ASTM C1107, "Standard Specification for Packaged Dry, Hydraulic-Cement Grout (Non-Shrink)"
- Canadian MTQ

DESCRIPTION

NS GROUT is designed for critical use where high strength, non-staining characteristics and positive expansion are required. NS GROUT contains only natural aggregate and an expansive cementitious binder. It is extremely flowable. When cured, it appears similar to concrete in appearance.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Non-staining natural aggregate for better appearance
- Excellent bearing
- Compatible with galvanic anodes (fluid consistency)
- Appearance of plain concrete
- Does not contain any added chloride ions
- Outstanding strength

PRIMARY APPLICATIONS

- Machine bases of all types
- Column baseplates
- Pumps and fans
- Compressors & motors
- Generators
- Anchor bolts

APPEARANCE

NS GROUT is a free flowing powder designed to be mixed with water. After mixing and placing, the color may initially appear much darker than the surrounding concrete. While this color will lighten up substantially as it cures and dries out, the grout may always appear somewhat darker than the surrounding concrete.

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Flowable Consistency	Fluid Consistency
ASTM C939/ CRD-C 621	Flow Rate	120% (Flow Table)	20 to 30 seconds (Flow Cone)
ASTM C109M* 2 in (50 mm) cubes	Compressive Strength	3 days . . . 4,500 psi (31 MPa) 7 days . . . 6,000 psi (41 MPa) 28 days . . . 8,500 psi (59 MPa)	3 days . . . 3,500 psi (24 MPa) 7 days . . . 5,000 psi (34 MPa) 28 days . . . 6,800 psi (47 MPa)
ASTM C827	Early Age Height Change	0.7%	1.1%
CRD-C 621	Expansion	3 days 0.02 % 7 days 0.02 % 14 days 0.03 % 28 days 0.03 %	3 days 0.01 % 7 days 0.03 % 14 days 0.05 % 28 days 0.05 %
ASTM C666	Freeze-Thaw Resistance Procedure A	300 cycles 97.1%	300 cycles 97.0%
*See ASTM C1107 Section 11.5	Setting Time	Initial 3 to 5 hours Final. 4 to 6 hours	

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Note: The contractor and engineer are encouraged to consult and review the Euclid Chemical bulletin: "Cementitious Grout Application Guide". The document offers instructions detailing the general installation of Euclid Chemical manufactured cement-based grout products. Important: If the contractor is not familiar with standard grout placement techniques, a pre-job meeting is suggested to review the project details unique to the particular job. Contact your local Euclid Chemical representative for additional information.

Mixing Water Guide: gal (L)/bag

Consistency	Estimated Water Content, 50 lb bag*
Fluid	1.1 to 1.2 gal (4.2 to 4.6 L)
Flowable	0.9 to 1.0 gal (3.4 to 3.8 L)
Plastic	0.8 to 0.9 gal (3.0 to 3.4 L)

**Do not add water in an amount that will cause bleeding or segregation. More or less water may be required to achieve a 25 second flow or the desired placing consistency, depending on temperature and other variables. Do not add sand or cement to the grout since this action will change its precision grouting characteristics.*

When NS GROUT will be placed at a depth over 5" (12.7 cm), up to 25 lb (11.3 kg) of pea gravel per 50 lb (22.7 kg) bag must be added to each bag of grout. Note that the water demand to achieve a certain flow level of the grout will change. Once the correct amount of water has been added to a clean mixing pail, mix the grout with a high speed drill and mixing paddle for 3 minutes. Quickly transport the grout to the placement area.

Application: See the "Cementitious Grout Application Guide" for installation means and methods.

PRECAUTIONS/LIMITATIONS

- Store materials in a dry place.
- Do not add sufficient water to promote bleeding of the grout.
- Use only potable water for mixing, and do not add admixtures or fluidifiers.
- Do not use this product at a flow cone rate of less than 20 seconds if checking flow rates on the job site (see CRD-C 611 or ASTM C939 for flow cone method).
- The application temperature range of NS GROUT is 45 to 85 °F (7 to 29 °C).
- Rate of strength gain is significantly affected at temperature extremes.
- Do not use material at temperatures that may cause premature freezing.
- Keep the grout from freezing until a minimum strength of 3000 psi (21 MPa) is reached.
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- NS GROUT can be mixed to a dry pack consistency. To achieve this, mechanically mix NS GROUT at a minimum water content of 0.5 gal per 50 lb bag (1.9L/22.7 kg).
- Add pea gravel when placing NS GROUT at a depth greater than 5" (12.7 cm).
- Proper curing is required.
- In all cases, consult the Safety Data Sheet before use.

Rev. 09.25

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.