



TAMMSCURE WB

WATER BASED RESIN CURING COMPOUND

PACKAGING

55 gal (208 L) drums
Code: THH3WBD55
5 gal (18.9 L) pails
Code: THH3WBP05

CLEAN UP

Warm, soapy water
(see "Clean-Up and Removal")

SHELF LIFE

2 years when stored properly

SPECIFICATIONS AND COMPLIANCES

- VOC Content: 47 g/L
- ASTM C 309, Types 1 and 1-D, Classes A & B
- AASHTO M 148, Types 1 and 1-D, Classes A & B

DESCRIPTION

TAMMSCURE WB is a water based dissipating curing compound that facilitates proper hydration of the concrete, then begins to break down upon exposure to traffic and UV light. After cleaning the concrete to completely remove TAMMSCURE WB, the surface is ready for the application of coverings, coatings, or sealers. TAMMSCURE WB is an unpigmented formulation. TAMMSCURE WB is also available with a red fugitive dye.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Use of this product ensures proper curing resulting in stronger, more wear-resistant concrete
- Helps to minimize dusting
- Available in a fugitive dye formulation
- Film breaks down when exposed to UV & traffic

COMMON METHODS

- Industrial pump-up sprayer or an airless industrial sprayer
- Short-nap roller

PRIMARY APPLICATIONS

- Curing interior or exterior* concrete
- Concrete that will later receive a covering or coating
- Where a long term membrane film is not desired on the concrete surface

* Product film will discolor when exposed to sunlight

APPEARANCE

TAMMSCURE WB may vary from off white to pale yellow. Color variation does not affect product performance. TAMMSCURE WB may turn a deeper amber color upon exposure to UV light.

APPLICATION PROPERTIES

These properties are based on laboratory conditions at at 73°F, 50% RH. Expect variation based on jobsite conditions.

Drying time:	1 to 2 hours
Foot Traffic:	2 to 4 hours
Wheel Traffic:	6 to 10 hours
Moisture Loss (ASTM C156):	< 0.55 kg/m ²

COVERAGE

For easy removal, do not apply at a thicker film than indicated. **Heavy or uneven application can cause yellowing and discoloration.**

Textured Concrete:	200 ft ² /gal (4.9 m ² /L)
Smooth Concrete:	400 ft ² /gal (9.8 m ² /L)

DIRECTIONS FOR USE

Surface Preparation: Use on freshly placed concrete as soon as possible after the concrete receives the final finishing, just as the water sheen disappears

Mixing: Thoroughly mix at slow speed before use to ensure best results and ease of application.

Application: TAMMSCURE WB should be applied with standard spray equipment. Small, hand operated units are adequate for small area applications, while power sprayers are recommended for mass concrete. When applying, coat uniformly and leave no gaps or overlapped areas.

Dissipation: TAMMSCURE WB will begin to break down approximately 4 to 6 weeks after application, but the exact time will vary depending on application rate, moisture level in the concrete, and the amount of exposure to UV light and construction traffic. **Floors to receive coatings, sealers and coverings must be cleaned thoroughly to ensure complete removal of TAMMSCURE WB.**

CLEAN-UP AND REMOVAL

Clean tools and equipment with warm, soapy water before TAMMSCURE WB dries.

The use of a heavy-duty floor cleaner such as EUCO CLEAN & STRIP is recommended to aid cleaning and removal. Scrub the floor with EUCO CLEAN & STRIP and stiff bristle scrubbers, then rinse well with clean water. After proper clean-up, follow the instructions of the sealer, coating or adhesive manufacturer for the recommended surface preparation for the particular product to be applied.

PRECAUTIONS/LIMITATIONS

- Do not apply TAMMSCURE WB to frozen or frosted surfaces, or when the temperature is expected to fall below 40 °F (4 °C) within 24 hours.
- Protect containers of this product from freezing.
- Do not dilute as the product is supplied at the proper consistency. Dilution will reduce curing efficiency.
- Complete removal of TAMMSCURE WB will be required before application of sealers, coatings, or toppings.
- Film may slightly discolor when exposed to sunlight
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 03.22

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.