



# THIN-TOP SUPREME

## SINGLE COMPONENT CEMENTITIOUS TOPPING & REPAIR MORTAR FOR THIN APPLICATIONS

**EUCLID CHEMICAL**

### PACKAGING

50 lb (22.7 kg) bags and pails

Code: 160T 50 (bag)

Code: 160T 05 (pail, MTO)

### APPROXIMATE YIELD

**50 lb (22.7 kg) unit:** 0.43 ft<sup>3</sup> (0.011 m<sup>3</sup>)  
per unit when mixed with 3.0 qt (2.8 L)  
of potable water.

### MINIMUM/MAXIMUM APPLICATION THICKNESS

1/16 to 3/8 inches (1.6 to 10 mm)

### CLEAN UP

 Clean tools and equipment with water  
before the material hardens.

### SHELF LIFE

2 years in original, unopened package

### SPECIFICATIONS AND COMPLIANCES

- Canadian Food Inspection Agency, MTQ and MTO

### DESCRIPTION

THIN-TOP SUPREME is a latex and microsilica modified cementitious mortar designed for use as a floor or deck topping at thicknesses of 1/16" to 3/8" (1.6 mm to 10 mm). This product is a single-component formula which incorporates a powder latex technology. It provides excellent durability under freeze-thaw cycling as well as reducing the ingress of water and de-icing salts. THIN-TOP SUPREME offers normal set times in a trowelable consistency for easy workability.

### PRODUCT CHARACTERISTICS

#### FEATURES/BENEFITS

- Provides a strong, wear resistant thin overlay
- Excellent durability in freeze-thaw cycles
- Contains an integral corrosion inhibitor
- Excellent bond to prepared concrete
- Reduces the penetration of water and de-icing salts for substrate protection
- Suitable for both interior and exterior use

#### COMMON METHODS

- Typically finished by float or broom

#### PRIMARY APPLICATIONS

- Parking decks
- Pavements
- Joints
- Marine structures
- Curbs and gutters
- Ramps
- Floors
- Walkways

#### APPEARANCE

THIN-TOP SUPREME is a free-flowing powder as packaged. After mixing and placing, the color may initially appear darker than the surrounding concrete. The color will lighten up substantially as it cures and dries out, though it may always appear somewhat darker than the surrounding concrete.

#### PHYSICAL PROPERTIES

Single component

Mixes with 2.75 to 3.25 quarts (2.6 to 3.08 L) of potable water per 50 lb (22.7 kg) bag/pail

Working Time: 30 to 40 minutes

Initial Set: 1 to 1.5 hour

Final Set: approximately 3 hours

 Unit Weight: 130 lb/ft<sup>3</sup> (2082 kg/m<sup>3</sup>)

Physical properties based on measurements at 70 °F in laboratory conditions.

The following coverage rates are approximations based on yield of a 50 lb (22.7 kg) unit mixed at standard consistency.

Application Thickness - inches (mm)	1/16 (1.6)	1/8 (3.2)	1/4 (6.4)	3/8 (9.5)
Coverage Area per Unit - ft <sup>2</sup> (m <sup>2</sup> )	82.5 (7.7)	41.2 (3.8)	20.6 (1.9)	13.7 (1.3)

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C109* 2" (50 mm) cubes	Compressive Strength	1 day . . . . . 2,000 psi (13.8 MPa) 7 days . . . . . 4,000 psi (27.6 MPa) 28 days . . . . . 6,000 psi (41.3 MPa)
ASTM C157	Linear Shrinkage	28 days . . . . . -0.15%
ASTM C348	Flexural Strength	7 days . . . . . 1,000 psi (6.9 MPa) 28 days . . . . . 1,200 psi (8.3 MPa)
ASTM C496	Split Tensile Strength	7 days . . . . . 300 psi (2.1 MPa) 28 days . . . . . 400 psi (2.8 MPa)
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles . . . 89% relative dynamic modulus

\*Mixed at 2.9 quarts (2.7 L) potable water per 50 lb (22.7 kg) bag

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

---

## DIRECTIONS FOR USE

**Surface Preparation:** Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP 4-6 in accordance with ICRI Guideline 310.2. Properly clean profiled area.

**Priming and Bonding (Saw Cut and Chipped Out Repairs):** Thoroughly clean any exposed reinforcing steel and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of THIN-TOP SUPREME to the SSD concrete substrate may be used for bonding.

**Priming & Bonding (Horizontal Toppings):** For the best adhesion to concrete, use EUCOFLOOR EPOXY PRIMER seeded with sand as the bonding coat. Refer to the EUCOFLOOR EPOXY PRIMER technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of THIN-TOP SUPREME to the saturated surface dry (SSD) concrete surface may be used for bonding. The topping material must be placed on the scrub coat before the scrub coat dries out.

**Mixing:** One 50 lb (22.7 kg) unit requires 2.75 to 3.25 qt (2.6 to 3.08 L) of potable water. All materials should be in the proper temperature range of 60 to 90 °F (15 to 32 °C). Single 50 lb (22.7 kg) units may be mixed with a drill and "jiffy" mixer. A paddle type mortar mixer or pan mixer may be used for large jobs. Add the appropriate amount of potable water to a clean mixing vessel, then gradually add the dry product. Do not exceed maximum water or add any additional additives. Mix for 3 to 5 minutes. Do not retemper.

**Placement:** Ambient and surface temperatures should be in the range of 45 to 100 °F (7 to 38 °C). Working time at 72 °F (22 °C) is approximately 30 to 40 minutes. To make repairs, completely fill repair area with material ensuring no voids and screed to match surrounding concrete. On large areas, use screed strips with a vibratory screed to level. For repairs and toppings thicker than 3/8" (10 mm), use CONCRETE-TOP SUPREME instead. Do not use THIN-TOP SUPREME for repairs less than 1/16" (1.6 mm) deep.

**Finishing:** This product is designed to be finished with a float or broom texture. Do not add water to the surface during the finishing operation. When placing under hot and windy conditions, the use of EUCOBAR evaporation retarder is recommended to prevent the loss of surface moisture. Always re-establish floor and slab joints when using this product as an overlay.

**Curing and Sealing:** Do not wet cure. Proper curing procedures are important to ensure the durability and quality of the repair. To mitigate surface cracking, cure the material with a high solids curing compound, such as SUPER AQUA-CURE VOX or SUPER DIAMOND CLEAR VOX. If a curing compound is not desired, cover with quality plastic sheeting for a minimum of 3 days. Do not use a solvent based curing compound on this product.

---

## PRECAUTIONS/LIMITATIONS

- Store in a dry place.
- Always mix full units.
- Do not use material at temperatures below 45 °F (7 °C) or above 100 °F (38 °C).
- Keep repair product from freezing until a minimum strength of 3,000 psi (21 MPa) is reached.
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- Do not use DURALPREP A.C. as a bonding agent for toppings and overlays done with THIN-TOP SUPREME.
- For repairs and toppings thicker than 3/8" (10 mm), use CONCRETE-TOP SUPREME.
- No heavy traffic until the product has cured.
- Do not wet cure. Do not use a solvent based curing compound on this product.
- In all cases, consult the Safety Data Sheet before use.

Rev. 09.25

**WARRANTY:** The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.